

# BOLIX SE



Compliant with the standard

## Super Flexible Adhesive

### USE:

- adhesive for fixing tiles (2 ÷ 10 mm),
- levelling compound for thickness up to 5 mm,
- for interior and exterior applications,
- for terraces, balconies and loggias,
- for wet rooms, including bathrooms, toilets, laundry rooms, shower stalls, public sanitary rooms,
- for walls and ceilings,
- heavy load surfaces such as a garages, workshops, industrial floors, halls, corridors, passageways,
- to install ceramic/stone tiles in EWI systems based on EPS

### SURFACE PREPARATION:

The surface must be structurally sound, even, clean of surface contaminants such as dust, grease, bitumen, algae and other barrier materials that may affect adhesion. New substrates should be fully cured:

- BOLIX SPN repair compound	at least 2 days
- BOLIX PC-B screed	at least 1 day - prior to laying ceramic tiles
	at least 2 days - prior to laying stone cladding
	at least 2 days
- BOLIX PC-S screed	
- BOLIX PC screed	at least 7 days
- anhydrite screeds	humidity ≤ 0,5%
- gypsum substrates	humidity ≤ 1,0%
- concrete, lightweight concrete	at least 3 months, humidity < 4%
- cement levellers, cement and lime-cement renders	at least 28 days, humidity < 4%

Remove limewash or colour wash. Even out minor irregularities with the adhesive BOLIX SE. Fill gaps and imperfections above 5 mm with the mortar BOLIX W and apply the BOLIX SN 20 self-leveller on floors. Prime porous surfaces with the BOLIX N Primer.

Sand any gypsum or anhydrite surfaces with coarse sandpaper, remove dust thoroughly and prime with BOLIX N.

Sand smooth and non-porous concrete substrates, terrazzo, existing ceramic or stone tiles, engineered wood plank or firm paint coats with coarse sandpaper and vacuum the sanding dust thoroughly. Prime with BOLIX BETOGRUNT.

Do not prime, when tiling over glass fibre reinforced base coats.

### PRODUCT PREPARATION:

Measure the clean water (5.75 ÷ 6.25 litre) into a suitable vessel/bucket and slowly add the adhesive while mixing using a low-speed drill until a homogeneous consistency is achieved. After 5 minutes and another stirring, the mixture is ready to use. Do not admix except water.

### APPLICATION:

To provide adhesion, firstly spread a thin layer of adhesive using the straight edge of a trowel. Follow immediately with the necessary thickness of the adhesive using a notched trowel to match the tile type and format. For tiling on the exterior, over heated substrates or floors subject to heavy loads and for installation of large format or thin tiles, spread a thin layer of the adhesive on the back of the tile (back-

### PRODUCT DESCRIPTION:

- increased adhesion (C2) to the surface
- reduced slump (T) - allows tiling from up to down
- extended open time (E)
- extreme flexibility (S1) - shrinkage compensating, accommodates and compensates for thermal and mechanical stresses
- formulated for large format tiles
- frost resistant
- suitable for difficult surfaces including drywall, OSB, tile on tile installation
- component of the insulation system with EPS as insulating material finished with ceramic/stone tiles

### SUBSTRATES:

Interior and exterior:

- cement screeds and floors,
- concrete, cellular or lightweight concrete, reinforced concrete
- cement and lime-cement renders
- solid masonry with full head and bed joints,
- existing terrazzo or concrete slabs,
- fibre cement cladding,
- waterproofing, including BOLIX HYDRO or BOLIX HYDRO-DUO,
- glass fibre reinforced base coat in the BOLIX T system.

Interior:

- "tile on tile" installation over existing ceramic and natural stone tiles,
- particle boards, OSB (≥ 22 mm), drywall,
- magnesite screed,
- gypsum renders, anhydrite,
- underfloor and wall heating.

### SUITABLE FOR:

Large, medium and small format tiles:

- ceramic (glazing, terracotta, porcelain, quarry)
- vitrified,
- composite tiles,
- stone, provided they are not prone to discolouration,
- concrete,
- ceramic mosaics, translucent tiles.

**Masz pytania?**  
 Zadzwoń!  
 801-650-222  
 Napisz!  
 serwis@bolix.pl

**BOLIX SA**  
 Ul. Stolarska 8  
 34-300 Żywiec  
 Tel. 33 475 06 00  
 Fax. 33 475 06 12

**Znajdź nas**  
[www.trwaleocieplenie.pl](http://www.trwaleocieplenie.pl)  
[www.facebook.com/bolixsa](https://www.facebook.com/bolixsa)  
[www.bolix.pl](http://www.bolix.pl)



# BOLIX SE

## Super Flexible Adhesive

buttering), using the straight edge of a trowel. Apply enough adhesive to set tiles before skinning occurs. Clean any soiled or dusty back tiles prior to tiling. Place the tile at the distance of the size of grout lines, making sure the tile is properly aligned with other tiles and firmly apply pressure to the face of the tile, while moving the tile back and forth. This helps to ensure that the mortar transfers to the back of the tile and that the tile is in an even plane with the adjacent tiles. The grout line size

will vary depending on tile size and conditions of use - do not butt joint. Skim off excess mortar before it sets.

### LIMITATIONS AND RECOMMENDATIONS:

- It is not recommended to wet or pre-wet tiles with water prior to installation.
- Do not apply to substrates, which are not damp-proofed against capillary absorption.
- Before application, cover or mask surfaces that are not to be used in the installation.
- Plan the surface area to be tiled over taking into consideration temperature and humidity conditions, surface type and workforce.
- Protect surfaces from direct sunlight exposure, precipitation and wind during installation of ceramic or stone tiles. Use scaffolding meshes.
- Low temperature, increased humidity and improper air circulation extend the drying and setting time of the product.
- Clean tools and hands with running water immediately after use. After drying difficulties with cleaning may be experienced.
- Wipe new stains off soiled surfaces with damp cloth. Hard stains may be removed only mechanically.
- Protect newly installed blocks from water penetration and frost until the mortar is fully set.
- Prior to tiling, waterproof wet rooms (showers, bathrooms, laundry rooms) with the liquid waterproofing membrane BOLIX HYDRO or BOLIX HYDRO DUO and the BOLIX HYDRO-T sealing tape. Waterproof the exterior surfaces (terraces, loggia and balconies) using the two-component compound BOLIX HYDRO-DUO and the BOLIX HYDRO-TW sealing tape.
- Expansion joints in the substrate must be extended through to the surface.
- Clean tools and hands with running water immediately after use. After drying difficulties with cleaning may be experienced.

### PRECAUTIONS:

Due to alkyd reaction of the product, avoid contact with skin and eyes. In case of eye contact, flush eyes with plenty of water and seek medical advice.

### TOOLS:

- Agitator or low-speed drill (400÷500 rpm) with mixing paddle
- Bucket
- Notch trowel (notch size should correspond to the tile size)
- Stainless steel scraper and trowel

### TECHNICAL DATA

The following technical data are for the temperature of +23 (±2)°C and relative air humidity of 50 (±5)%. Under other conditions the technical data may vary.

#### Ambient and surface temperature at application and setting:

from +5°C to +25°C

#### Relative humidity at application and setting:

up to 80%

#### Bulk density:

approx. 1,20 g/cm<sup>3</sup>

#### Colour:

grey

#### Adhesive thickness:

2÷10 mm

#### Pot life:

up to 3h

#### Open time:

approx. 30 min.

#### Adjusting time:

approx. 30 min.

#### Grouting/Walkable:

after min. 24h

#### Full load:

after min. 3 days

#### Temperature resistance:

-30°C ÷ +70°C

#### Packaging:

25 kg bag

#### No. of containers per pallet and net weight:

48 / ca. 1200 kg

#### Shelf life:

12 months from the date of production provided on the packaging

### NOMINAL COVERAGE:

approx. 1.20 kg/m<sup>2</sup> for 1 mm thick adhesive coat

Coverage depends on surface levelling, type of tiles and thickness of adhesive layer. To determine precise coverage perform a test patch on the substrate.

### STORAGE:

Store in intact containers in temp. between +5°C and +25°C. Protect from damp. Store away from the reach of children.

### COMPOSITION:

Hydraulic binders, polymers, fine mineral and synthetic fillers modifiers.

BOLIX S.A. guarantees product quality but has no control over its application and use. BOLIX takes no responsibility for contractors' and distributors' performance. The information supplied herein is given in good faith based on our current knowledge and latest application methods. The information provided cannot replace designer's and contractor's expertise and does not dismiss anyone from observing good practice and the OHS regulations. Should you have any further queries, carry out necessary tests or contact BOLIX Customer Technical Support. The publication of this Technical Data Sheet renders older editions invalid.



#### Masz pytania?

Zadzwoń!  
801-650-222

Napisz!  
serwis@bolix.pl

#### BOLIX SA

Ul. Stolarska 8  
34-300 Żywiec  
Tel. 33 475 06 00  
Fax. 33 475 06 12

#### Znajdź nas

www.trwaleocieplenie.pl  
www.facebook.com/bolixsa  
www.bolix.pl